



## Safety Data Sheet

Page 1 of 9

Loctite Super Glue Power Flex Control

SDS No. : 398516

V001.2

Date of issue: 19.12.2024

### Section 1. Identification of the substance/preparation and of the company/undertaking

**Product name:** Loctite Super Glue Power Flex Control

**Intended use:** Super glue

**Supplier:**  
Henkel Australia Pty Ltd  
135-141 Canterbury Road  
Kilsyth, Victoria, 3137  
Australia

**Phone:** +61 (3) 9724 6444

**E-mail address of person responsible for Safety Data Sheet:** SDSinfo.Adhesive@henkel.com

### Section 2. Hazards identification

#### Classification of the substance or mixture

Hazardous according to the criteria of Safe Work Australia.

#### GHS Classification:

<u>Hazard Class</u>	<u>Hazard Category</u>	<u>Target organ</u>
Flammable liquids	Category 4	
Skin irritation	Category 2	
Serious eye irritation	Category 2A	
Target Organ Systemic Toxicant - Single exposure	Category 3	respiratory tract irritation
Acute hazards to the aquatic environment	Category 3	

#### Hazard pictogram:



**Signal word:** Warning

- Hazard statement(s):** H227 Combustible liquid.  
H315 Causes skin irritation.  
H319 Causes serious eye irritation.  
H335 May cause respiratory irritation.  
H402 Harmful to aquatic life.
- Precautionary Statement(s):**
- Prevention:** P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.  
P261 Avoid breathing mist/vapours.  
P264 Wash hands thoroughly after handling.  
P271 Use only outdoors or in a well-ventilated area.  
P273 Avoid release to the environment.  
P280 Wear protective gloves/protective clothing/eye protection/face protection.
- Response:** P302+P352 IF ON SKIN: Wash with plenty of water.  
P304+P340+P312 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing. Call a POISON CENTER or physician if you feel unwell.  
P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.  
P332+P313 If skin irritation occurs: Get medical advice/attention.  
P337+P313 If eye irritation persists: Get medical advice/attention.  
P362+P364 Take off contaminated clothing and wash it before reuse.  
P370 + P378 In case of fire: Use dry sand, dry chemical or alcohol-resistant foam to extinguish.
- Storage:** P403+P233 Store in a well-ventilated place. Keep container tightly closed.  
P405 Store locked up.
- Disposal:** P501 Dispose of contents/container to an appropriate treatment and disposal facility in accordance with applicable laws and regulations.

**Dangerous Goods information:**

Not classified as Dangerous Goods according to the criteria of the Australian Code for the Transport of Dangerous Goods by Road and Rail (ADG Code).

**Section 3. Composition / information on ingredients**

**General chemical description:** Mixture

**Identity of ingredients:**

Chemical ingredients	CAS-No.	Proportion
Ethyl 2-cyanoacrylate	7085-85-0	60- <= 100 %
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane	119-47-1	< 0.3 %

**Section 4. First aid measures**

- Ingestion:** Ensure that breathing passages are not obstructed. The product will polymerise immediately in the mouth making it almost impossible to swallow. Saliva will slowly separate the solidified product from the mouth (several hours).
- Skin:** Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such as a spoon, preferably after soaking in warm soapy water.  
Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate enough heat to cause a burn.  
Burns should be treated normally after the adhesive has been removed from the skin.  
If lips are accidentally stuck together apply warm water to the lips and encourage maximum wetting and pressure from saliva inside the mouth.  
Peel or roll lips apart. Do not try to pull the lips apart with direct opposing action.

<b>Eyes:</b>	If the eye is bonded closed, release eyelashes with warm water by covering with wet pad. Cyanoacrylate will bond to eye protein and will cause periods of weeping which will help to debond the adhesive. Keep eye covered until debonding is complete, usually within 1-3 days. Do not force eye open. Medical advice should be sought in case solid particles of cyanoacrylate trapped behind the eyelid cause any abrasive damage.
<b>Inhalation:</b>	Move to fresh air, consult doctor if complaint persists.
<b>First Aid facilities:</b>	Eye wash and safety shower Normal washroom facilities
<b>Medical attention and special treatment:</b>	Treat symptomatically.  Surgery is not necessary to separate accidentally bonded tissues. Experience has shown that bonded tissues are best treated by passive, non-surgical first aid. If rapid curing has caused thermal burns they should be treated symptomatically after adhesive is removed.

### Section 5. Fire fighting measures

<b>Suitable extinguishing media:</b>	Foam, extinguishing powder, carbon dioxide. Fine water spray
<b>Improper extinguishing media:</b>	High pressure waterjet
<b>Combustion behaviour:</b>	Combustible Liquid Keep away from heat, spark, and open flames.
<b>Decomposition products in case of fire:</b>	Thermal decomposition can lead to release of irritating gases and vapors. carbon monoxide Carbon dioxide. Oxides of nitrogen.
<b>Special protective equipment for fire-fighters:</b>	Wear full protective clothing. Fire fighters should wear positive pressure self-contained breathing apparatus (SCBA).

### Section 6. Accidental release measures

<b>Personal precautions:</b>	Ensure adequate ventilation. Avoid skin and eye contact. Wear protective equipment.
<b>Environmental precautions:</b>	Do not let product enter drains.
<b>Clean-up methods:</b>	Do not use cloths for mopping up. Flood with water to complete polymerization and scrape off the floor. Cured material can be disposed of as non-hazardous waste. Dispose of contaminated material as waste according to Section 13.

## Section 7. Handling and storage

<b>Precautions for safe handling:</b>	Prevent contact with eyes, skin and clothing. Do not breathe vapor and mist. Wash thoroughly after handling. Avoid contact with fabric or paper goods. Contact with these materials may cause rapid polymerization which can generate smoke and strong irritating vapors, and cause thermal burns.
<b>Conditions for safe storage:</b>	Store in a cool, dry, well-ventilated area. For optimum shelf life store in original containers under refrigerated conditions at 2 - 8°C (35.6 - 46.4 °F). Keep away from heat and direct sunlight. Keep container tightly sealed. Refer to AS 1940: The Storage and Handling of Flammable and Combustible Liquids.

## Section 8. Exposure controls / personal protection

### National exposure standards:

None

<b>Engineering controls:</b>	Ensure good ventilation/extraction.
<b>Eye protection:</b>	Wear protective glasses.
<b>Skin protection:</b>	Protective clothing that covers arms and legs. The use of chemical resistant gloves such as Nitrile is recommended. Polyethylene or polypropylene gloves are recommended when using large volumes. Do not use PVC, rubber or nylon gloves. Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed then the gloves should be replaced.
<b>Respiratory protection:</b>	If inhalation risk exists, wear a respirator or air supplied mask complying with the requirements of AS/NZS 1715 and AS/NZS 1716.

## Section 9. Physical and chemical properties

<b>Appearance:</b>	Colourless / Colorless ClearColourless / Colorless Clear
<b>Odor:</b>	IrritatingIrritating
<b>pH:</b>	Not applicable, Product reacts with water.
<b>Melting point / freezing point:</b>	Not applicable, Product is a liquid
<b>Specific gravity:</b>	1.1
<b>Boiling point:</b>	> 100 °C (> 212 °F)> 100 °C (> 212 °F)
<b>Flash point:</b> (no method / method unknown)	80 - 93 °C (176 - 199.4 °F)
<b>Vapor pressure:</b> (; 20 °C (68 °F); 25 °C (77 °F))	< 0.2 mm hg < 0.5 mbar
<b>Vapor density:</b>	3
<b>Density:</b>	1.10 g/cm <sup>3</sup>
<b>Viscosity (dynamic):</b>	>= 2,000 mPa.s(Cone and plate; Instrument: Physica MC 100 (or equivalent), Cone MK 22; 25 °C (77 °F); Shear gradient: 20 s-1; Method: ;; LCT STM 738; Rheological Data from flow curves)>= 2,000 mPa.s(Cone and plate; Instrument: Physica MC 100 (or equivalent), Cone MK 22; 25 °C (77 °F); Shear gradient: 20 s-1; Method: ;; LCT STM

738; Rheological Data from flow curves)

**Section 10. Stability and reactivity**

<b>Stability:</b>	Stable under recommended storage conditions.
<b>Conditions to avoid:</b>	Keep away from sources of ignition and naked flames.
<b>Incompatible materials:</b>	Rapid exothermic polymerization will occur in the presence of water, amines, alkalis and alcohols.
<b>Hazardous decomposition products:</b>	Thermal decomposition can lead to release of irritating gases and vapors.  carbon monoxide Carbon dioxide. Oxides of nitrogen.

**Section 11. Toxicological information****Acute toxicity:**

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	LD50 LD50	> 5,000 mg/kg > 2,000 mg/kg	oral  dermal		rat rabbit	equivalent or similar to OECD Guideline 423 (Acute Oral toxicity) equivalent or similar to OECD Guideline 402 (Acute Dermal Toxicity)
Bis(2-hydroxy-3-tert- butyl-5- methylphenyl)methane 119-47-1	LD50 LD50	> 10,000 mg/kg > 10,000 mg/kg	oral  dermal		rat rat	not specified not specified

**Skin corrosion/irritation:**

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	slightly irritating	24 h	rabbit	equivalent or similar to OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

**Serious eye damage/irritation:**

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	irritating		rabbit	equivalent or similar to OECD Guideline 405 (Acute Eye Irritation / Corrosion)

**Respiratory or skin sensitization:**

Hazardous components CAS-No.	Result	Test type	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	not sensitising	Guinea pig maximisation test	guinea pig	equivalent or similar to OECD Guideline 406 (Skin Sensitisation)

**Germ cell mutagenicity:**

Hazardous components CAS-No.	Result	Type of study / Route of administration	Metabolic activation / Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	negative negative negative	bacterial reverse mutation assay (e.g Ames test) in vitro mammalian chromosome aberration test mammalian cell gene mutation assay	with and without with and without with and without		equivalent or similar to OECD Guideline 471 (Bacterial Reverse Mutation Assay) OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test) OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)

**Section 12. Ecological information**

**General ecological information:** Do not empty into drains / surface water / ground water.

**Ecotoxicity:** H402 Harmful to aquatic life.

**Toxicity:**

Hazardous components CAS-No.	Value type	Value	Acute Toxicity Study	Exposure time	Species	Method
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	LC50	Toxicity > Water solubility	Fish	96 h	Oryzias latipes	OECD Guideline 203 (Fish, Acute Toxicity Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	EC50	Toxicity > Water solubility	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	EC50	Toxicity > Water solubility	Algae	72 h	Pseudokirchneriella subcapitata (reported as Selenastrum capricornutum)	OECD Guideline 201 (Alga, Growth Inhibition Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	NOEC	Toxicity > Water solubility	Algae	72 h	Pseudokirchneriella subcapitata (reported as Selenastrum capricornutum)	OECD Guideline 201 (Alga, Growth Inhibition Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	EC50	Toxicity > Water solubility	Bacteria	3 h	activated sludge	OECD Guideline 209 (Activated Sludge, Respiration Inhibition Test)

**Persistence and degradability:**

Hazardous components CAS-No.	Result	Route of application	Degradability	Method
------------------------------	--------	----------------------	---------------	--------

Ethyl 2-cyanoacrylate 7085-85-0	not readily biodegradable.	aerobic	57 %	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	under test conditions no biodegradation observed	aerobic	0 %	OECD Guideline 301 C (Ready Biodegradability: Modified MITI Test (I))

**Bioaccumulative potential / Mobility in soil:**

Hazardous components CAS-No.	LogPow	Bioconcentration factor (BCF)	Exposure time	Species	Temperature	Method
Ethyl 2-cyanoacrylate 7085-85-0	0.776				22 °C	EU Method A.8 (Partition Coefficient)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1		320 - 780	60 d	Cyprinus carpio		OECD Guideline 305 E (Bioaccumulation: Flow-through Fish Test)
Bis(2-hydroxy-3-tert-butyl-5-methylphenyl)methane 119-47-1	6.25				20 °C	OECD Guideline 107 (Partition Coefficient (n-octanol / water), Shake Flask Method)

**Section 13. Disposal considerations**

**Waste disposal of product:**

Cured adhesive: Dispose of as water insoluble non-toxic solid chemical in authorised landfill or incinerate under controlled conditions.  
Dispose of in accordance with local and national regulations.  
Contribution of this product to waste is very insignificant in comparison to article in which it is used

**Disposal for uncleaned package:**

After use, tubes, cartons and bottles containing residual product should be disposed of as chemically contaminated waste in an authorised legal land fill site or incinerated.  
Disposal must be made according to official regulations.

**Section 14. Transport information**

**Road and Rail Transport:**

**Dangerous Goods information:**

Not classified as Dangerous Goods according to the criteria of the Australian Code for the Transport of Dangerous Goods by Road and Rail (ADG Code).

**Marine transport IMDG:**

Not dangerous goods

**Air transport IATA:**

UN no.:	3334
Proper shipping name:	Aviation regulated liquid, n.o.s. (Cyanoacrylate ester)
Class or division:	9
Packing group:	III
Packing instructions (passenger)	964
Packing instructions (cargo)	964
Additional Information IATA:	Not more than 500 ml (each inner package) - Unrestricted

**Section 15. Regulatory information****SUSMP Poisons Schedule**

None

**AIC:**

All components are listed or are exempt from listing on the Australian Inventory of Industrial Chemicals or Introduced under AICIS.

**Section 16. Other information****Abbreviations/acronyms:**

ADGC - Australian Dangerous Goods Code  
IMDG: International Maritime Dangerous Goods code  
IATA-DGR: International Air Transport Association – Dangerous Goods Regulations  
STEL - Short term exposure limit  
TWA - Time weighted average  
AIIC - Australian Inventory of Industrial Chemicals (AIIC)  
AICIS - Australian Industrial Chemicals Introduction Scheme

**Reason for issue:**

Reviewed MSDS. Reissued with new date. involved chapters: 1-16

**Date of previous issue:**

13.03.2020

**Disclaimer:**

The percentage weight (% w/w) of ingredients is not to be taken as a specification guaranteed by Henkel Australia Pty. Limited, but only as an approximate guide to the content of hazardous ingredients in the material. The information contained herein does not constitute a guarantee by Henkel Australia Pty. Limited concerning the properties of the material.

The information contained in the Safety Data Sheet is offered in good faith and has been developed from what is believed to be accurate and reliable sources. The information is offered without warranty, representation, inducement or licence and Henkel Australia Pty. Limited assumes no legal responsibility for reliance upon same. Henkel Australia Pty. Limited disclaims any liability for loss, injury or damage incurred in connection with the use of the material or its associated Safety Data Sheet.

This information is not to be construed as a representation that the material is suitable for any particular purpose or use except those conditions and warranties implied by either Commonwealth or State statutes. Customers are encouraged to make their own enquiries as to the material's characteristics and, where appropriate, to conduct their own tests in the specific context of the material's intended use.

No warranty or representation of any kind is given with respect to the substantive or export laws of any other jurisdiction or country. Please confirm that the information provided herein conforms to the substantive export or other law of any other jurisdiction prior to export. Please contact Henkel Product Safety and Regulatory Affairs for additional assistance.



